

# Neodur<sup>®</sup> Primer 1K

## One-component, fast-drying polyurethane primer

### Description

**Neodur<sup>®</sup> Primer 1K** is a one-component, fast-drying polyurethane primer, ideal for cementitious surfaces and asphalt substrates

### Fields of application

Prior to the application of resinous systems (**Epoxol<sup>®</sup>**, **Neopox<sup>®</sup>**, **Neodur<sup>®</sup>**) on surfaces of:

- Asphalt
- Cement
- Metal

### Properties - Advantages

- Excellent adhesion on various substrates
- Exhibits flexibility which makes it ideal for resinous flooring applications on asphalt substrates
- Fast-drying, enabling the application of both the primer and the first layer of the coating / system in one day
- Easy to apply (one-component – cures with the ambient humidity)



### Appearance

Transparent

### Packing

Set (A+B) of 5L

### Technical characteristics

Density (EN ISO 2811-1)	0,98kg/L (±0,05)
Adhesion strength (EN 1542)	>2,5N/mm <sup>2</sup>
<b>Consumption:</b> • 180-220ml/m <sup>2</sup> per layer on asphalt substrate • 150-200ml/m <sup>2</sup> per layer on cementitious substrate • 125-140ml/m <sup>2</sup> per layer on metallic surfaces	

### Application conditions

Substrate moisture content	<4%
Relative air humidity (RH)	<70%
Application temperature (ambient - substrate)	+12°C min. / +35°C max.

### Curing details

Drying time (+25°C, RH 50%)	1,5 hours
Dry to recoat - overcoat (+25°C, RH 50%)	4 hours
Full hardening (+25°C, RH 50%)	24 hours

*\* Low temperatures and low humidity during application and/or curing prolong the above times, while high temperatures and high humidity reduce them*

## Instructions for use

### Substrate preparation

The substrate must be stable, clean, dry & protected from rising moisture, as well as free of dust, oil, grease, dirt and any loose or poorly adhering material. Loose friable material must be completely removed by appropriate mechanical or chemical means.

#### Asphalt substrate

The substrate must be thoroughly prepared by high pressure water-jetting and allowed to dry completely.

#### Cementitious surfaces

The cementitious substrate must be properly prepared mechanically (e.g. grinding, shot blasting, milling etc.) to smooth out the irregularities, achieve an open texture surface and ensure the optimum bonding.

The surfaces must be as smooth and flat as possible, as well as continuous (ie without voids, cracks etc.)

Otherwise, they should be repaired and leveled with suitable repairing materials.

### Application

After thorough stirring, **Neodur® Primer 1K** is applied undiluted on the surface by roller, brush or airless spray. In case of increased substrate porosity, an additional priming layer may be required.

## Special notes

- **Neodur® Primer 1K** should not be applied under wet conditions, or if wet conditions are expected to prevail during the application or the curing period of the product
- The substrate temperature must be at least 3°C above dew point, in order to avoid condensation issues
- If a time period of more than 24 hours elapses between successive layers, it is recommended to lightly sand the surface of the previous layer, in order to avoid possible adhesion problems of the next one



<b>Appearance</b>	Transparent
<b>Packing</b>	5L in metal cans
<b>Cleaning of tools – Stains removal</b>	By <b>Neotex® 1021</b> or <b>Neotex® PU 0413</b> immediately after the application. In case of hardened stains, by mechanical means only.
<b>Volatile organic compounds (V.O.C.)</b>	V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AhSB: 750g/l (Limit 1.1.2010) - V.O.C. content of the ready-to-use product <750g/l
<b>UFI code</b>	SSF0-90YP-K008-MT06
<b>Versions</b>	<b>Neotex® PU Primer</b> , one-component, polyurethane fast-drying primer for the stabilization of old floors, preventing dust generation
<b>Storage stability</b>	12 months, if kept in the original sealed packaging, protected from frost, humidity and exposure to solar radiation.

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX® SA. It is offered as a service to designers and contractors to help them find potential solutions. However, as a supplier, NEOTEX® SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

**HEADQUARTERS - PLANT**  
V. Moira str., Xiropigado  
**LOGISTICS SALES & CENTER**  
Loutsas str., Voro

P.O. Box 2315, GR 19600  
Industrial Area Mandra  
Athens, Greece  
T. +30 210 5557579

**NORTHERN GREECE BRANCH**  
Ionias str., GR 57009  
Kalochori, Thessaloniki, Greece  
T. +30 2310 467275